

Collected Data Sheet



PONACOM ABS Industrial Compounds

Product	Product description	Density	MFI (220°C - 10 kg)	Tensile Modulus	Charpy impact notched Charpy + 23°C	Izod impact strength notched Izod + 23°C	Vicat B
		EN ISO 1183 g/cm ³	EN ISO 1133 g/10 min	EN ISO 527-2 Mpa	EN ISO 179-1/1eA kJ/m ²	EN ISO 180/1 kJ/m ²	EN ISO 306 °C
PONACOM 7315 industrial black	medium flowing	1,06	14 - 16	2400	9 - 11	10 - 13	95
PONACOM 7310-12 industrial black	high impact	1,06	9 - 13	2200	11 - 13	12 - 15	92
PONACOM 7410 black	standard	1,06	9 - 13	2400	9 - 11	10 - 13	95
PONACOM 7410-12 black	high impact	1,06	9 - 13	2200	11 - 13	12 - 15	92
PONACOM 7420 black	easy flowing	1,06	18 - 22	2400	9 - 11	10 - 13	95
PONACOM 7510 deep black	standard	1,06	10 - 14	2400	9 - 11	10 - 13	95
PONACOM 7515 deep black	medium flowing	1,06	14 - 16	2400	9 - 11	10 - 13	95
PONACOM 7520 deep black	easy flowing	1,06	18 - 22	2400	9 - 11	10 - 13	95
PONACOM 7920 grey	easy flowing	1,1	18 - 22	2300	9 - 11	10 - 13	95

This list contains only a selection of all types. Please send us your request. We will send our offer.